

TDS: (Technical Data Sheet)



GLOBAL TRANSFORMER OIL

HIGHLY REFINED HYDROTREATED ELECTRICAL INSULATING OIL (inhibited)

Product Description

GLOBAL TRANSFORMER OIL is designed based on highly refined, hydro-treated paraffinic base stock with excellent response to anti-oxidant with high degree of purity and stability. It is suitable for use in any kind of electrical applications including power and distribution transformers, converters, rectifier and switchgears.

Applications

- Power transformers, distribution transformers, converters, rectifier, circuit breakers and switchgear

Features and Benefits

- Excellent oxidation stability with selected anti-oxidant provides extended oil life and stable operation
- Proved anti-corrosion performance with very low Sulfur contents
- Good low temperature fluidity provides continuous operation regardless of any weather condition
- Effective cooling and heat transfer performance and very good dielectric properties
- No impurities such as water, dissolved gas, DBDS, suspended solid and PCB

Performance levelTypical

- IEC 60296:2012: Table 2 transformer oil (T), (I)
- C 2301 Class 1

Properties

Properties	Method	Units	TRANSFORMER OIL T	TRANSFORMER OIL I
Appearance			Clear	Clear
Density @ 15°C	ISO 3675 or ISO 12185	g/cm ³	0.8285	0.8225
Viscosity at -30°C	ISO 3104	cSt	284	269
Viscosity at 40°C	ISO 3104	cSt	7.492	7.483
Viscosity at 100°C	ISO 3104	cSt	2.222	2.218
Pour Point	ISO 3016	'C	-55	-55
Flash Point	ISO 2719	'C	159	151
Acidity	IEC 62021-1 or 62021-2	mg KOH/g	< 0.01	< 0.01
Oxidation Stability	IEC 61125:1992 (C)			
- Total Acidity		mg KOH/g	0.1	< 0.01
- Sludge		wt%	< 0.01	< 0.01
- DDF @ 90°C			0.0066	0.0057
Inhibitors of IEC 60666	IEC 60666	wt%	0.05	0.3
Water Content	IEC 60814	mg/kg	18	17
Breakdown Voltage (untreated/treated)	IEC 60156	kV	72 / 80	81 / 81
Dissipation Factor at 90°C	IEC 60247 or IEC 61620		0.0145	0.0003
Corrosive Sulphur	DIN 51353		Non Corrosive	Non Corrosive
PCBs	IEC 61619	mg/kg	Undetectable	Undetectable
DBDS	IEC 62697-1	mg/kg	Undetectable	Undetectable
Metal Passivator additives	IEC 60666	mg/kg	Undetectable	Undetectable
Furfural and related compounds	IEC 61198	mg/kg	Undetectable	Undetectable

The statements made in this publication are according to our present knowledge. They do not absolve the user from own examinations. A legally binding assurance of certain properties or suitability for a specific use cannot be derived from our statements. Possibly existing laws and regulations concerning the handling and use of our products have to be observed by the receiver of our products himself.